



EMEROX® Polyols Improve Your Potting Formulation's Cost and Sustainability

EMEROX Polyols are engineered for performance and sustainable by nature due to their high bio-based content. These hydrophobic polyol esters are designed to work in a range of polyurethane applications to offer chemical and hydrolytic resistance, reduce system cost, and meet environmental and supply chain sustainability objectives.

The EMEROX Polyols listed below are effective alternatives to hydroxyl functional polybutadiene for use in polyurethane potting compounds. They offer superior low temperature performance, low water solubility and moisture vapor transmission, excellent thermal stability, and good electrical properties.

EMEROX 14801 and EMEROX 14803 are engineered polyols that provide a flexible hydrophobic backbone with a low glass transition temperature for applications where increased hydrophobicity and low temperature performance is required. EMEROX 14511 is an engineered polyol with lower functionality that provides a slightly softer cured product where flexibility is advantageous and is Certified Biobased under the USDA BioPreferred® Program.

PRODUCT NAME	HYDROXYL NUMBER	SPECIFIC GRAVITY	VISCOSITY cP @25°C	T _g (°C)	FN (Calc.)	BIO-BASED CONTENT	APPLICATION DESCRIPTION
EMEROX® 14511	110	1.14	1,400	-58	2.0	78*	1000 MW azelate linear diol for general purpose prepolymer CASE applications. PPG 1000 alternative.
EMEROX® 14801	105	0.96	2,600	-59	2.2	90**	1000 MW for superior hydrophobic performance in CASE applications. Hydroxy-terminated polybutadiene alternative.
EMEROX® 14803	55	0.96	16,000	-54	2.2	90**	2000 MW for superior hydrophobic performance in CASE applications. Hydroxy-terminated polybutadiene alternative.



*USDA Certified Biobased Product.

**Bio-based content is an estimate, pending final testing.

Key Benefits

- Superior low and high temperature performance
- Hydrophobic structure with good chemical and moisture resistance
- Very low moisture vapor transmission rates
- Good electrical properties
- Comparable performance to petrochemical polyols, but with high renewable content
- Produced from well-established, readily available natural feedstocks
- Certified by the USDA BioPreferred® Program

Performance attributes of a potting compound utilizing EMEROX® I45I I or EMEROX® I480 I with pMDI and butane diol in an unpigmented system which has been cured for 7 days at 25°C.

EMEROX® Polyol only

	EMEROX® I45I I	EMEROX® I480 I
Viscosity, cP @ 25°C (ASTM D 2393)		
Polyol	1437	2600
Polyisocyanate	18	18
Initial Mixed	958	1560

	EMEROX® I45I I	EMEROX® I480 I
Density (Lbs./Gal. (g/ml) @ 25°C)		
Polyol	9.51 (1.14)	8.01 (0.96)
Polyisocyanate	10.10 (1.21)	10.10 (1.21)
Mixed	9.68 (1.16)	8.51 (1.02)

Rheology (@ 25°C)			
Low shear	20 s ⁻¹ , cP	1435	2596
High shear	120 s ⁻¹ , cP	1422	2584

Compatibility with other Polyol Resins		
PolyBD	Partial	Partial
Castor Oil	Incompatible	Compatible
Azelates	Compatible	Compatible
Adipates	Compatible	Incompatible

Mixed System/Cured Elastomer Physical Properties

Mix Ratio (Parts polyol to one Part polyisocyanate)		
By Weight	1.89	1.62
By Volume	2	2

Gel Time (min.)		
175 g @ 25°C	1.53	3.67

Tg, °C (ASTM D3418)		
	-14	-28

Coefficient of Thermal Expansion(CTE), μm/m-°C, (ASTM E831)		
α1 (below Tg)	79	110
α2 (above Tg)	224	209

Tensile Properties at 25°C (ASTM D638)		
Tensile Strength (psi)	1190	3047
Tensile Modulus (psi)	1052	1690
% Elongation	343	142
Tear (pli)	301	561

Mixed System/Cured Elastomer (cont.)

	EMEROX® I45I I	EMEROX® I480 I
Water Absorption & Transmission		
1 week (wt. % @ 75°C)	3.66	2.43
4 weeks (wt. % @ 75°C)	6.33	3.32
MVTR (g/m ² /day)	59.4	24.6

Hardness Development (Shore)		
Cured 24 hours @ 70°C	83A / 38D	97A / 55D

Electrical Properties

Dielectric Constant (ASTM D150)		
20 Hz	6.72	3.70
1 kHz	5.94	3.36
10 kHz	5.33	3.19
100 kHz	3.03	4.67
1 MHz	4.13	2.91
10 MHz	5.09	3.81

Dissipation Factor (ASTM D150)		
20 Hz	0.106	0.025
1 kHz	0.064	0.036
10 kHz	0.083	0.037
100 kHz	0.090	0.034
1 MHz	0.084	0.028
10 MHz	0.089	0.029

Resistivity (ASTM D257)		
Surface Resistivity, Ohm	1.0 X 10 ¹²	2.6 X 10 ¹²
Volume Resistivity, Ohm-cm	1.2 X 10 ¹⁴	3.6 X 10 ¹³

Dielectric Strength (V/mil)		
	111.5	117.0

To request a sample or to find out more about our EMEROX® Polyols, contact EFP.Americas@emeryoleo.com or visit www.emeryoleo.com/polyols

Disclaimer: The content in this document is provided on an "as is" and "as available" basis purely for informational purposes and, unless and to the extent specifically agreed otherwise for a sales transaction, does not constitute any warranty, whether express, implied or statutory, including but not limited to warranties or guarantees of merchantability, fitness or suitability for a particular purpose nor any representations of a binding nature. EMERY OLEOCHEMICALS EXPRESSLY DISCLAIMS ANY RESPONSIBILITY FOR THE SUITABILITY OF THE PRODUCTS FOR ANY SPECIFIC OR PARTICULAR PURPOSES INTENDED BY THE USER. Suggestions for the use and application of the products and guide formulations are for informational purposes only and you are advised to carry out any necessary steps to test the suitability of the products for your intended processes and purposes. You are solely responsible for compliance with all applicable laws and regulations in use of the products including any third party intellectual property rights and shall bear all liability or risk arising from use of the products. All indications marked with a TM or ® symbol are trademarks belonging to legal entities within the Emery Oleochemicals group of companies.

Release 10/2022